

AMENDMENT UNDER 37 C.F.R. § 1.111,
AMENDMENT UNDER 37 C.F.R. § 1.48(b) AND
REQUEST FOR DECLARATION OF INTERFERENCE
UNDER 37 C.F.R. § 1.607
U.S. Appln. No. 09/942,763

Please amend page 1 of the specification, first paragraph as follows:

This application is a continuation of Application No. 08/472,189, filed June 7, 1995, now abandoned, which is a continuation of Application No. 08/285,652, filed August 3, 1994, now U.S. Patent No. 5,478,783, which is a continuation-in-part of United States application No. 08/190,883, filed February 3, 1994, now abandoned.

Bl Page 9, delete Table I and insert new Table I as follows:

Table I
Example

| | 1 | 2 | 3 | 4 | 5 | 6 | 7 | 8 | 9 | 10 | 11 |
|----------------------------------------------|------|------|------|------|------|------|------|------|------|------|------|
| Total Iron as Fe ₂ O ₃ | 0.5 | 0.55 | 0.55 | 0.31 | 0.61 | 0.56 | 0.56 | 0.54 | 0.57 | 0.51 | 0.53 |
| FeO | 0.11 | 0.14 | 0.13 | 0.08 | 0.14 | 0.13 | 0.14 | 0.13 | 0.16 | 0.12 | 0.09 |
| % of Total Iron as Fe ²⁺ | 25 | 29 | 27 | 27.2 | 26 | 25 | 27 | 27 | 31 | 27 | 19 |
| Se | 2 | 7 | 9 | 3 | 2 | 2 | 1 | 1 | <1 | 2 | 5 |
| Co ₃ O ₄ | 10 | 10 | 19 | 20 | 12 | 5 | 13 | 24 | 10 | 12 | 13 |
| TiO ₂ | 1.6 | 0.33 | 0.34 | - | - | - | - | - | 1.0 | - | - |
| NiO | - | - | 15 | - | - | 23 | - | 31 | - | - | - |
| LT | 72 | 71 | 71 | 75 | 73 | 76 | 74 | 72 | 74 | 71 | 71 |
| DSHT | 53 | 50 | 51 | 63 | 51 | 54 | 52 | 53 | 50 | 52 | 57 |
| UTV | 36 | 45 | 47 | 59 | 51 | 51 | 51 | 53 | 53 | 40 | 46 |
| a* | -5.1 | -4.8 | -5.2 | -2.0 | -4.7 | -4.9 | -5.3 | -5.0 | -6.2 | -5.2 | -1.9 |
| b* | 7.5 | 3.2 | 2.4 | 0.2 | 1.5 | 1.9 | 0.3 | -1.0 | -0.8 | 5.5 | 4.1 |
| \D | 565 | 546 | 529 | 499 | 512 | 518 | 498 | 499 | 494 | 560 | 569 |
| Purity | 6.9 | 2.4 | 1.7 | 0.8 | 1.3 | 1.3 | 2.3 | 3.3 | 3.6 | 4.8 | 4.0 |

IN THE CLAIMS:

Claims 1 and 17 are cancelled.

1 13. (Amended) A neutral gray colored glass composition having a base glass portion comprising: